

TECHNICAL DATA SHEET for FO-POXY (Br)

DESCRIPTION : Excellent ability for repairing and rebuilding of damaged and worn out bronze machinery parts and equipments. Has good conductance of energy. This compound is not machinable.

APPLICATION : Repair of damaged bronze parts, outer vessel coating.

PROPERTIES :

CURE TIME	(MINS.)	-	120
COMPRESSIVE STRENGTH	(KGS/CM ²)	-	910
TENSILE STRENGTH	(KGS/CM ²)	-	250
FLEXURAL STRENGTH	(KGS/CM ²)	-	450
HARDNESS	(SHORE D)	-	88

TEMP. RANGE : UPTO 180°C

CHEMICAL REACTIVITY : Doesn't react with common industrial gases, acids, reagents and solvents.

ADDITIONAL INFORMATION : Can be prepared as per client specification.
Coverage Area : 850 sq.cm / Kg for 5 mm product thickness

MANUFACTURED BY :

AQUADRA FORSPEC PVT. LTD., Mumbai, India

Tel. : 022- 2884 5705

Fax : 022- 2887 2661

E-mail : aquadra@vsnl.com

The information contained and the recommendations made in this data sheet are based upon data collected and believed by us to be correct. However, no guarantee or warranty of any kind, expressed or implied, is made herein with respect to the merchandise described and we assume no responsibility for the results or the use thereof.