

FO-POXY (CGC)

Cold Galvanizing Compound

DESCRIPTION :

Zinc galvanizing compound, available in single pack. It can be brushed or sprayed using an airless spray gun. It is used to protect surfaces from corrosion. Post-cured it can also be painted.

The deposit forms a galvanic cell with the base metal, so in case the coating gets scratched the deposit sacrifices itself to form an impermeable zinc oxide film, thereby protecting the surface.

APPLICATION :

- Protection of ferrous surfaces from corrosion in corrosive environment and near coastal areas.
- Repair Hot Dip Galvanized surfaces damaged during shearing, cutting, welding or during construction / fabrication.
- Protection of Weldments which have a different electrical potential than the base metal.
- Protection of outdoor Electrical Equipments viz. transformer, reactors, capacitors, etc.
- As a protective base coating in Bridges, Pipelines, Tanks, Channel frames, etc.
- For structure protection of Oil rigs, Transmission Tower, Ships, Sewage Plants, etc.

PROPERTIES :

Dry Time	(mins.)	:	30
Cure Time	(Hours)	:	24
Mass Density	(gms./c.c.)	:	2.9
% Solids of Liquid Coating	(%)	:	88
Metallic Zinc Content	(by wt.)	:	over 92 % (in dry film)
Theoretical Coverage	(sq. mtr. / ltr.)	:	approx. 10-12
Max. Temperature resistance	(°C)	:	200

MANUFACTURED BY :

AQUADRA FORSPEC PVT. LTD., Mumbai, India

Tel. : 022- 2884 5705

Fax : 022- 2887 2661

E-mail : aquadra@vsnl.com

The information contained and the recommendations made in this data sheet are based upon data collected and believed by us to be correct. However, no guarantee or warranty of any kind, expressed or implied, is made herein with respect to the merchandise described and we assume no responsibility for the results or the use thereof.