

# **FO-POXY (G)**

## **GLASS LINING REPAIR COMPOUND**

### **DESCRIPTION**

Machinable Cold Weld Compound, having excellent adhesion with glass lining. It brings down the maintenance and operational cost drastically and is all set to revolutionize the Glass lining Industry.

### **APPLICATION**

Repair of vessel where the Glass lining has been partially or completely worn out. It can also be used for rebuilding glass lined equipments such as spindles, impellers, flanges, etc.

### **PROPERTIES**

CURE TIME	(MINS.)	- 60
COMPRESSIVE STRENGTH	(KGS/CM <sup>2</sup> )	- 1303
TENSILE STRENGTH	(KGS/CM <sup>2</sup> )	- 325
FLEXURAL STRENGTH	(KGS/CM <sup>2</sup> )	- 597
HARDNESS	(SHORE D)	- 95
WITHSTANDING PRESSURE	(KGS/CM <sup>2</sup> )	- 110
MAXIMUM TEMPERATURE	(°C)	- 250

### **CHEMICAL RESISTANCE**

Doesn't react with common industrial gases, acids, reagents & solvents.

### **ADDITIONAL INFORMATION**

Can be prepared as per client specification.

Coverage Area : 1070 sq.cm. / Kg for 5 mm product thickness.

### **MANUFACTURED & MARKETING BY :**



**AQUADRA FORSPEC  
PVT. LTD.**

**Tel.: 022- 2884 5705 Fax : 2887 2661 Email : aquadra@vsnl.com**

The information contained and the recommendations made in this data sheet are based upon data collected and believed by us to be correct. However, no guarantee or warranty of any kind, expressed or implied, is made herein with respect to the merchandise described and we assume no responsibility for the results or the use thereof.